



* Piston rod must be protected against paint, dirt and damage.

Force tested statically, testing speed 750mm/min

Extension force $F1 = 40N \begin{matrix} +25N \\ -0N \end{matrix}$

Test condition: Piston rod downwards

Surface treatment

- A = CeramPro
- B = black powder coated
- C = zinc plated steel
- D = aluminium

This drawing is not subject to the revision service.

Without our specifically acceptance, this drawing is not allowed to be copied or given to other persons.

scale: drawing not in scale position:

Note: All dimensions in mm

	date	name
edited	05.03.2026	W.Grimm
check.	05.03.2026	M.Munz

gas spring $\varnothing 8/22$

Bansbach easylift GmbH
Barbarossastr. 8
D-73547 Lorch/Württemberg

BONOT91-150-426--001/040N

sheet